AMPP Senior-Internal-Corrosion-Technologist Practice Questions

Shared by Cardenas on 12-11-2026

For More Free Questions and Preparation Resources

Check the Links on Last Page

Question 1

Question Type: MultipleChoice

A reinforced coating is

Options:

A- equally resistant to movement and impact as a non-reinforced coating.
B- equally resistant to abrasion and impact as a non-reinforced coating.
C- less resistant to movement, abrasion, and impact than a non-reinforced coating.
D- more resistant to movement, abrasion, and impact than a non-reinforced coating.

Answer:

D

Question 2

Question Type: MultipleChoice

Surface preparation of concrete is performed using:

Options:

A- Methods that are exactly the same as steel
B- Methods that are completely different to steel
C- Methods that have been modified for concrete
D- Methods that are the same as wood

Answer:

C

Question 3

Question Type: MultipleChoice

When performing Inspection in accordance with ASTM D 4138 the Inspector will use:

Options:

A- A set of 14 pencils of varying hardness
B- A destructive paint inspection Tooke gauge
C- A mechanical adhesion tester
D- A hardness tester

Answer:

B

Question 4

Question Type: MultipleChoice

Which standards are generally established by private-sector bodies and are available for use by any person or organization, private or government?

Options:

A- Consensus
B- Mandatory
C- Defector
D- Voluntary

Answer:

A

Question 5

Question Type: MultipleChoice

You can use magnifiers to examine all of the following EXCEPT

Options:

A- Surface profile
B- Surface cleanliness

C- Blisters
D- Mill scale

Answer:

B

Question 6

Question Type: MultipleChoice

In powder coatings, when the particles of powder begin to flow but are not fully liquid, they are in what stage?

Options:

A- Flow stage
B- Wetting stage
C- Cure stage
D- Get stage

Answer:

A

Question 7

Question Type: MultipleChoice

Individuals conducting Coating Surveys should:

Options:

A- Always be NACE Level 3 Certified Inspectors
B- Always be NACE or 5SPC Protective Coating Specialists
C- Always be experienced Specification Writers
D- Always be trained and experienced Coating Industry

Answer:

A

Question 8

Question Type: MultipleChoice

When performing an adhesion test in accordance with ASTM D 3359 where the Dry Film Thickness Is approximately 10 mils, the Inspector should use:

Options:

A- Method A-X Cut
B- Method A - Cross Hatch
C- Method B-X cut
D- Method B - Cross Hatch

Answer:

A

To Get Premium Files for Senior-Internal-Corrosion-Technologist Visit

https://www.p2pexams.com/products/senior-internal-corrosion-technologist

For More Free Questions Visit

https://www.p2pexams.com/ampp/pdf/senior-internal-corrosion-technologist

